



Beyard Slate Co.,Ltd.

No.1 Lianmeng Industry Zone,Hengtang town,Xingzi county, Jiangxi Proovince,332808

Tel: +86-792-2595148

Fax:86-792-2597089

BEYARD

Web:www.china-beyard.com

Email:BeyardSlate@hotmail.com

Test Report For Beyard's Natural Slate

SOURCE AND APPEARANCE

Slate from Xingzi,China.

Appearance: dark grey face with a little shading, no easily perceptible fossils.

Properties: colour variations always occur to some extent, even in the same batch. The upper surface occasionally has a little shading and back often is kibble for the sake of level up or not depends on the demand. This is unavoidable and no complaints will be accepted about this.

Finishes:

Roofing:Split,Drill or Jag Side

Tiles: Split, Calibrated or honed

Cladding: Split, Calibrated or Stick

Mosaic: Split, Calibrated or Stick



Beyard Slate Co.,Ltd.

No.1 Lianmeng Industry Zone,Hengtang town,Xingzi county, Jiangxi Proovince,332808

Tel: +86-792-2595148

Fax:86-792-2597089

BEYARD

Web:www.china-beyard.com

Email:BeyardSlate@hotmail.com

CHARACTERISTICS

Compressive Strength: 1229kg/cm²,

Modulus of Rupture: 365kg/cm²,

Abrasion Resistance:1.14g/cm²,

Polish degree:90,

Water Absorption: 0.04%,

Enduring acid rate:98.52%,

Xiao rigidity:63,

Containing weight 2.71T/m³,

Radioactivity intensity: less than 10, below 1220 °C,

Bake granule weight: 0.4-0.8g/cm³ . .

USE

Due to its excellent property,this natural stone is suitable for all use: roofing,floor, wall,billiard slate and stair covering in both domestic housing and in public buildings with moderate to intensive commercial use.